

Table S1 The Various Proportions of the Epoxy Resin Systems.

Samples	E12/g	DCD/g	2-MI/g	PA-DAD/g
Neat Epoxy	100	2.5	0.5	0
EP/10%PA-DAD	100	2.5	0.5	10
EP/15%PA-DAD	100	2.5	0.5	15
EP/20%PA-DAD	100	2.5	0.5	20
EP/25%PA-DAD	100	2.5	0.5	25
EP/30%PA-DAD	100	2.5	0.5	30