

Table S1 Elemental and industrial analysis of coconut residues.

Sample	Content (wt%)						
	C	H	N	Ash	Moisture	Volatiles	Fixed carbon
En	44.68	5.92	1.06	3.57	3.2	65.0	29.5
Me	43.78	5.85	0.28	3.77	2.3	61.8	34.7
Ep	46.16	5.93	0.56	3.39	2.7	62.3	32.2