

Supplementary Table S4. Temperature conditions for preparing biochar from hemp biomass

Step	Temperature (°C)	Rate (°C/min)	Holding time (min)
T1	25	0	–
T2	100	15	60
T3	Expected pyrolysis temperature (500, 700, and 800 °C)	20	90
T4	25	20	–